



17 Hampshire Drive, Unit 8
Hudson, NH 03051

www.conductivecompounds.com

Innovative Chemistry For High-Tech Applications

Phone: (603) 595-6221

Fax: (603) 595-6228

C-200

CARBON FILLED ELECTRICALLY CONDUCTIVE SCREEN PRINTABLE INK/COATING

C-200 is a unique electrically conductive carbon filled ink utilizing a vinyl copolymer binder. C-200 is designed for screen printing in flex and additive circuit applications such as membrane switches. C-200 is tough, scuff resistant and has excellent adhesion to both treated polyester and polyimide substrates, and glass. Crease resistance is outstanding when used on these substrates. C-200 will adhere for use on indium tin oxide (ITO) sputtered surfaces.

C-200 is designed to give a good balance between long open time in screen printing operations and short drying time. Conductive Compounds, Inc. can adjust the rheology of C-200 to allow for more open time, or quicker drying, in order to accommodate different screening and drying operations.

C-200 can be blended with AG-800 silver filled inks for specific resistance values, and is compatible with our UV curable dielectrics, encapsulants and conformal coatings. It is suitable for screen printing traces and discreet resistance pads and as an overprint for silver conductive traces.

TYPICAL PROPERTIES

Appearance	Thixotropic black colored paste
Viscosity- Brookfield SC4-14 spindle, Shear rate of 20 rpm	< 30,000 cps
Thixotropic Ratio	3.0
Drying Schedule	< 5 minutes at 290° F. (May be longer or shorter depending upon heat source and air flow)
Shelf Life	6 months in unopened container
Total % NV Solids	33% +/- 2%
Hegman Gage	<50.0 μ
Volume Resistivity (ref. ASTM D-257)	0.5 Ω -cm
Surface Resistivity	<50 Ω /Square

Conductive Compounds, Inc. offers custom formulating to tailor this material to your application.

NOTE: Although the above properties are accurate to the best of our knowledge Conductive Compounds, Inc. makes no guarantees for customer specifications established in applications where this product is used. Customer assumes responsibility for determining fitness of use in their particular application.

MORE INFORMATION ON REVERSE SIDE OF SHEET

C-200
CARBON FILLED ELECTRICALLY CONDUCTIVE
SCREEN PRINTABLE INK/COATING

APPLICATION GUIDELINES

For screening, a monofilament polyester (157 to 230 mesh) or a stainless steel (165 to 325 mesh) screen is recommended, with emulsion thickness between .001" and .004". A polyurethane squeegee with a Shore 'A' durometer between 60 and 70 is recommended. Always mix ink thoroughly before using, as carbon will settle to the bottom.

For thinning and cleanup, use butyl cellosolve acetate or dibasic ester solvents. If faster drying time is required, contact Conductive Compounds, Inc. for solvent recommendations.

If solvent based inks are left on screens for any length of time, the ink will gradually thicken as solvent evaporates. If ink is to be left on an inactive press for any length of time, solvent evaporation can be minimized by pooling the ink into a small area instead of leaving it spread out over a large area. Pooling the ink reduces the surface area, thus slowing the drying process. Always check the viscosity of ink that has been recovered from a screen and add small amounts of solvent while mixing thoroughly to restore viscosity. Solvent can be added to reclaim thickened ink, as long as the ink has not dried and hardened completely.

It is essential that all residual solvent be removed from this ink once it is applied. Incomplete drying will cause the ink to appear dry on the surface while trapping solvent underneath the surface. Over time, this trapped solvent will migrate out of the ink, and can cause adhesion problems with any material (such as dielectrics) applied over the ink.

To check completeness of drying, evaluate the point-to-point resistance along one of the screened conductive paths after one pass through the drying oven or one cycle in a batch-drying oven. Run the substrate through another drying cycle. Measure the point-to-point resistance again along the same path and compare it to the original reading. If the resistance decreases by less than 10%, then the ink is essentially dry after the first drying cycle or pass through the oven. If the resistance decreases by more than 10%, then more drying time is required to completely remove the solvent.

When blending C-200 ink with AG-800 silver ink for specific resistance ranges, be sure to mix the materials thoroughly before screening.

The above guidelines are intended to provide a starting point for evaluation. Conductive Compounds, Inc. recognizes that each customer's manufacturing process is unique, and we can customize the rheology to conform to the process parameters. We are also available to provide on-site technical assistance to resolve your processing issues. Call us to discuss your application in more detail.

Revised 6/15/11